

Technical Data



COPPER ANTI -SEIZE PASTE **HIGH TEMPERATURE ANTI-SEIZE LUBRICANT**



COPPER PASTE is a high temperature anti-seize lubricant. A soft, copper-coloured paste, based on micronised copper powder and synergistic anti-oxidant, anti-corrosion and anti-wear additives suspended in a premium grade stable oil. It is an effective anti-seize formulation, preventing metal-to-metal contact, seizing, galling, and fretting corrosion.

FEATURES

- Reduces friction and wear, even when the base oil has already evaporated
- High pressure and high temperature resistance
- Ensures accurate assembly
- Enables easy disassembly of threaded parts, gaskets and flanges, even after long operational periods
- Threaded parts remain in good condition and can be re-used
- Separating film ensures favourable release behaviour of the threaded connections
- Excellent sealing even in corrosive atmospheres
- Resistant to hot and cold water
- Lead-free and nickel-free
- Aerosol formulation does not contain chlorinated solvents and uses hydrocarbon propellant
- Does not migrate, even when heated to 370°C

APPLICATIONS

An effective anti-seize lubricant for:

- Bolts, nuts, pins
- Guides for brakes
- Brake adjusters
- Splines
- Flanges, flange seals
- Exhaust screw connections
- Sliding sleeves / shafts
- To absorb disk brake noise
- Screw connections on hydraulic equipment
- Bushings, fittings
- Spark plugs
- Wheel bolts
- Pipeline connections
- Linkages
- Press fits

DIRECTIONS

- The surfaces to be treated should be clean, dry and grease-free. Wire brushed parts and clean with an oil-free solvent like Amberklene FE10
- A thin, even film should be applied either by spraying or by brushing

- Assembled parts (gear teeth, screws, ...) can slowly be put in motion.
- Avoid mixing with other products.
- Test before use on plastics or rubber.
- Do not use on energised equipment, oxygen systems or in presence of acetylene.
- Use aerosol only in ventilated areas.

TYPICAL PRODUCT DATA (without propellant)

Appearance	:	Homogenous, copper colored
Aerosol properties	:	
Flash point (open cup)	:	< 0°C
Boiling range (solvent)	:	60-95°C
Vapour density (vs. air=1)	:	3
Specific gravity @ 20°C	:	0.81
Dry film properties		
Specific gravity @ 20°C	:	0.99
Flash point (open cup)	:	> 200°C
Dropping point	:	none
NLGI consistency	:	1 - 2
Low temperature stability	:	-30°C
Temperature resistance *		
lubrication	:	300°C
anti-seize	:	1100°C
Hot water resistance (DIN 51807 T1, 40°C, 90°C)	:	1
Corrosion (DIN 51802)	:	0/0
Four Ball Wear (DIN 51350 T5, 1h, 500N)	:	0.5 mm
Packaging	:	12 x 400 ml

* Grease decomposition temperature is 300°C. Anti-seize properties of copper particles are conserved up to approximately 1100°C.

STORAGE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 72 months with correct storage. Aerosols should always be stored below 50°C, away from direct heat and naked flame.

HEALTH AND SAFETY

Health and Safety sheet available separately.

MISREPRESENTATION ACT 1967

TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

CRC Industries UK Limited, Wylds Road, Bridgwater, Somerset, TA6 4DD

Tel: +44 (0) 1278 727200

Fax: +44 (0) 1278 425644

Web: www.ambersil.com

E-mail: sales.uk@crcind.com